## PWL<sub>2</sub>



Reference No: 2024/01/04

Both sides treated white pigmented BOPP film.

## **Properties**

- · High protection against light for food packaging
- Whiteness eliminates need of white ink, therefore it reduces problems of residual solvents from printing

## **Applications**

White film for surface print and also lamination, cold seal and release lacquer applications.

PROPERTIES	TEST CONDITIONS		UNITS	TYPICAL VALUES				
THICKNESS			μ	20	25	28	35	38
			Gauge	80	100	112	140	152
THICKNESS TOLERANCE			%	5				
UNIT WEIGHT	ASTM D 2673		g / m²	18±1.4	22.5±1.7	25.2±2.0	31.5±2.4	34.2±2.8
YIELD	ASTM D 2673		m² / kg	55.6±4	44.4±3	39.7±2.5	31.7±2	29.2±2
HAZE	ASTM D 1003		%					
GLOSS	ASTM D 2457		%	55 ± 5				
OPTICAL DENSITY	MACBETH			$0.38 \pm 0.02$ $0.46 \pm 0.02$			0.02	
COEFFICIENT OF FRICTION*	ASTM D 1894	B/B*		< 0.45				
		B/M*		< 0.25				
TENSILE STRENGTH	ASTM D 882	MD	N/mm²	120 ± 20				
		TD	IN/IIIIII	270 ± 50				
ELONGATION AT BREAK	ASTM D 882	MD	%	190 ± 40				
		TD	70	45 ± 10				
HEAT SEAL TEMPERATURE	3 Bar / 0.5 Sec		°C					
SEAL STRENGTH	130°C / 3 Bar / 0.5 Sec		N / 15 mm					
WVTR	ASTM F 1249 38°C / 90% RH		g / m² / day	7.0	6.0	5.5	5.0	4.0
TREATMENT LEVEL	ASTM D 2578		dyne / cm	≥ 38 (front side), ≥ 36 (back side)				
HEAT SHRINKAGE	130°C / 7 mln	MD	%	≤ 5.0				
		TD		≤ 3.0				

<sup>\*</sup>B: Back side

\*M: Metal

The above information is the result of laboratory test which are applied on samples from standart production. Since the varying conditions under which our products used are beyond our control, all of the above results are without guarantee and warranty.

POLİBAK Plastik Film San. ve Tic.A.Ş. AOSB Izmir-TURKIYE Phone: +90 232 3767970 Fax: +90 232 3767730 E-Mail: polibak@polibak.com.tr www.polibak.com.tr

<sup>\*</sup>All COF values are dynamic results