

# CPP285-P (Developmental Grade)



One side very low temperature heat sealable with high seal strength, other side treated, dart resistant non oriented polypropylene film.

## Properties

- Excellent mechanical and optical properties
- High toughness and softness
- Excellent seal integrity & seal strength
- Very Low SIT

## Applications

Designed especially for lamination to other flexible films, where needs high heat seal strength and hermetic seal application as an alternative to PE.

Also designed for winter conditions, and an improved dart drop is required.

PROPERTIES	TEST CONDITIONS	UNITS	TYPICAL VALUES	
THICKNESS	.....	μ	50	
		Gauge	200	
THICKNESS TOLERANCE	.....	%	5	
UNIT WEIGHT	ASTM D 2673	g / m <sup>2</sup>	45.3	
YIELD	ASTM D 2673	m <sup>2</sup> / kg	22.1	
HAZE	ASTM D 1003	%	< 5.0	
GLOSS	ASTM D 2457	%	85 ± 5	
OPTICAL DENSITY	MACBETH	.....	...	
COEFFICIENT OF FRICTION*	ASTM D 1894	B/B*	.....	< 0.45
		B/M*		< 0.30
TENSILE STRENGTH	ASTM D 882	MD	N/mm <sup>2</sup>	45 ± 20
		TD		25 ± 5
ELONGATION AT BREAK	ASTM D 882	MD	%	500 ± 100
		TD		500 ± 100
HEAT SEAL TEMPERATURE	3 Bar / 0.5 Sec	°C	85 - 145	
SEAL STRENGTH	100°C / 3 Bar / 0.5 Sec	N/15mm	> 15	
WVTR	ASTM F 1249 38°C / 90% RH	g / m <sup>2</sup> / day	<7.0	
TREATMENT LEVEL	ASTM D 2578	dyne / cm	> 36	
HEAT SHRINKAGE	130°C / 7 min	MD	%	0 ± 2.5
		TD		0 ± 2.5

\*B : Back side

\*All COF values are dynamic results

\*M : Metal

The above information is the result of laboratory test which are applied on samples from standart production. Since the varying conditions under which our products used are beyond our control, all of the above results are without guarantee and warranty.

POLİBAK Plastik Film San. ve Tic.A.Ş. AOSB Izmir-TURKIYE

Phone : +90 232 3767970 Fax : +90 232 3767730

E-Mail : polibak@polibak.com.tr www.polibak.com.tr

Reference No : 2025/07/00