

CPP395 (Developmental Grade)



Both sides heat sealable, one side treated, non oriented polypropylene film for deep freeze application.

Properties

- Excellent mechanical and optical properties
- High toughness and softness
- Excellent resistance to tearing and perforation
- Very low SIT

Applications

Designed especially for bag manufacture where high tear resistance is required.
Used in resistant down to -18°C frozen food packaging.

PROPERTIES	TEST CONDITIONS		UNITS	TYPICAL VALUES			
THICKNESS		μ	25	30	40	50
			Gauge	100	120	160	200
THICKNESS TOLERANCE		%	5			
UNIT WEIGHT	ASTM D 2673		g / m ²	22.6	27.2	36.2	45.3
YIELD	ASTM D 2673		m ² / kg	44.3	36.8	27.6	22.1
HAZE	ASTM D 1003		%	< 4.0		< 5.0	
GLOSS	ASTM D 2457		%	80 ± 5			
OPTICAL DENSITY	MACBETH				
COEFFICIENT OF FRICTION*	ASTM D 1894	B/B*	< 0.30			
		B/M*		< 0.25			
TENSILE STRENGTH	ASTM D 882	MD	N/mm ²	45 ± 10			
		TD		25 ± 5			
ELONGATION AT BREAK	ASTM D 882	MD	%	500 ± 100			
		TD		500 ± 100			
HEAT SEAL TEMPERATURE	3 Bar / 0.5 Sec		°C	95 - 145			
WVTR	ASTM F 1249 38°C / 90% RH		g / m ² / day	<9.5	<8.5	<7.0	
TREATMENT LEVEL	ASTM D 2578		dyne / cm	> 36			
HEAT SHRINKAGE	130°C / 7 min	MD	%	0 ± 2			
		TD		0 ± 2			

*B : Back side

*All COF values are dynamic results

*M : Metal

The above information is the result of laboratory test which are applied on samples from standart production. Since the varying conditions under which our products used are beyond our control, all of the above results are without guarantee and warranty.

POLİBAK Plastik Film San. ve Tic.A.Ş. AOSB İzmir-TURKIYE

Phone: +90 232 3767970 Fax: +90 232 3767730

E-Mail: polibak@polibak.com.tr www.polibak.com.tr

Reference No : 2023/11/00