

Non heat sealable, metallized side treated, pearlised metallized BOPP film.

Properties

- High yield due to low density
- Aluminium deposited side for printing
- Excellent aspect

Applications

Designed especially for bottle labelling, and can also be used for cold seal and release lacquer applications.

**Both sides treated version is available as PRLM.*

PROPERTIES	TEST CONDITIONS		UNITS	TYPICAL VALUES	
THICKNESS		μ	35	38
			Gauge	140	152
THICKNESS TOLERANCE		%	5	
UNIT WEIGHT	ASTM D 2673		g / m ²	25.2 ± 1.0	27.3 ± 1.0
YIELD	ASTM D 2673		m ² / kg	39.7 ± 1.5	36.6 ± 1.5
HAZE	ASTM D 1003		%	
GLOSS	ASTM D 2457		%	
OPTICAL DENSITY	MACBETH		Opaque > 0.55 / Metallized > 2.4	
COEFFICIENT OF FRICTION*	ASTM D 1894	B/B*	< 0.60	
		B/M*		< 0.30	
TENSILE STRENGTH	ASTM D 882	MD	N/mm ²	90 ± 20	
		TD		200 ± 50	
ELONGATION AT BREAK	ASTM D 882	MD	%	170 ± 30	
		TD		45 ± 10	
HEAT SEAL TEMPERATURE	3 Bar / 0.5 Sec		°C	
SEAL STRENGTH	130°C / 3 Bar / 0.5 Sec		N / 15mm	
WVTR	ASTM F 1249 38°C / 90% RH		g / m ² / day	≤ 1.5	
OTR	ASTM D 3985 23°C / 0% RH		cm ³ /m ² /day	≤ 200	
HEAT SHRINKAGE	130°C / 7 min	MD	%	≤ 5.0	
		TD		≤ 3.0	

*B : Back side

*All COF values are dynamic results

*M : Metal

The climatic and storage conditions may influence the metallised surface treatment.

In-line corona treatment is recommended for lamination. An adequate primer on the metallized surface is suggested for printing.

The above information is the result of laboratory test which are applied on samples from standart production. Since the varying conditions under which our products used are beyond our control, all of the above results are without guarantee and warranty.

POLİBAK Plastik Film San. ve Tic.A.Ş. AOSB İzmir-TURKIYE

Phone : +90 232 3767970 Fax : +90 232 3767730

E-Mail : polibak@polibak.com.tr www.polibak.com.tr

Reference No : 2016/07/03